

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 499 206 A2

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **92102265.3**(51) Int. Cl.⁵: **C08G 65/32, C07C 229/18**(22) Date of filing: **11.02.92**

(30) Priority: **12.02.91 JP 41324/91**
30.04.91 JP 128417/91
30.04.91 JP 128418/91

(43) Date of publication of application:
19.08.92 Bulletin 92/34

(84) Designated Contracting States:
DE FR GB


(71) Applicant: **NIPPON PAINT CO., LTD.**
1-2, Oyodokita 2-chome Kita-ku
Osaka-shi(JP)

(72) Inventor: **Ohshima, Toshiyuki**
4-25-20 Ayukawa
Ibaraki-shi, Osaka-fu(JP)
Inventor: **Ishibashi, Hideo**
24-10 Nakakandacho
Neyagawa-shi, Osaka-fu(JP)
Inventor: **Tamura, Rie**
2-1-1-611 Shoji
Toyonaka-shi, Osaka-fu(JP)
Inventor: **Yamamoto, Satoshi**
2-10-10 Nagaohigashimachi
Hirakata-shi, Osaka-fu(JP)
Inventor: **Izumo, Takaharu**
789 Yamazaki, Shimamoto-cho
Mishima-gun, Osaka-fu(JP)

(74) Representative: **Kinzebach, Werner, Dr. et al**
Patentanwälte Reitstötter, Kinzebach und
Partner Sternwartstrasse 4 Postfach 86 06 49
W-8000 München 86(DE)

(54) **Polyamine compositions containing secondary amine functions.**

(57) Polyoxyalkylene polyamine or aromatic diamines or xylylenediamines are modified by subjecting to the Michael reaction with an ethylenically unsaturated monomer having an electron-withdrawing group to convert the primary amino groups at least in part to a secondary amino group of the formula:



wherein R is a hydrogen atom or methyl, and Y is an electron-withdrawing group. The modified amines find use in the manufacture of plastics such as polyurea elastomers or polyurea RIM.

EP 0 499 206 A2

BACKGROUND OF THE INVENTION

This invention relates to a novel polyamine composition for use as a raw material in the manufacture of plastics such as in the reaction injection molding (RIM) of polyurea and the like.

Polyoxyalkylene polyamines find use as a raw material in the manufacture of polyurea elastomers and RIM as well as in hardening epoxy resins. It has been known that when polyoxyalkylene polyamines are modified to have a plurality of secondary amino groups at the terminal ends of the molecule, the resulting products will exhibit excellent reactivity with polyisocyanate compounds compared with the corresponding primary polyoxyalkylene polyamines and, therefore, the resulting polyurea products may have excellent properties.

Aromatic diamines and xylylene diamines also find use in the polyurea RIM and the like. The modification of their primary amino groups to secondary amino groups also result in beneficial effects on the reactivity with polyisocyanates as well as properties of the resulting polyurea products.

One of prior art methods for producing secondary amine-terminated polyoxyalkylene polyamines is disclosed in Japanese Laid Open Patent Application (Kokai) Nos. 38425/1990 and 127425/1989. This method includes hydrogenolytic aminolysis of the corresponding polyoxyalkylene polyols with a primary amine. This method suffers from certain disadvantages in that the reaction takes place only under high pressure and high temperature in an autoclave in the presence of a catalyst such as Raney nickel. Another known method is disclosed in Japanese Laid Open Patent Application (Kokai) No. 153931/1990 and includes alkylation of the corresponding primary polyamines with alkyl halides. This method also suffers from certain disadvantages in that a portion of the starting primary amine is necessarily consumed for binding the hydrogen halide by-product or an excess of acid-binding agent such as alkali metal hydroxides must be added. Besides, the conversion rate to secondary amino groups is relatively low and the alkylating agent is relatively expensive.


The alkylation method may also find its application to the production of secondary aromatic diamines and xylylenediamines from the corresponding primary amines as disclosed, for example, in Japanese Laid Open Patent Application (Kokai) Nos. 311116/1990 and 251515/1990, respectively. In addition to various deficiencies as discussed above, alkylation of primary diamines of this type proceeds stepwise and one of primary amino groups may be alkylated only with difficulty once the other primary amino group has been alkylated. Accordingly, this method is utilized in practice for the production of asymmetric diamines in which one amino group is primary and the other is secondary.

All of the above discussed prior art methods generally give a secondary amine of which second hydrocarbon substituent is an alkyl or aralkyl radical free of a functional group. In contrast with this, Japanese Laid Open Patent Application (Kokai) No. 251515/1990 discloses the Michael reaction of a polyamine with an acrylic or methacrylic monomer to convert low molecular weight, straight chain, aliphatic primary diamines or alicyclic primary diamines to the corresponding secondary diamines. The reaction products have a secondary amino group of which second hydrocarbon substituent has a functional group originating from the acrylic or methacrylic monomer. In our experiments, however, it has been revealed that the secondary amine content of the products of this method is unsatisfactorily low particularly when the monomer is a methacrylic monomer.

Accordingly, a need exists for a secondary polyamine composition and the method of making the same which eliminate or ameliorate deficiencies of the prior art compositions and methods.


SUMMARY OF THE INVENTION

The present invention provides a polyamine composition for use in the manufacture of plastics comprising a member selected from the group consisting of a polyoxyalkylene polyamine, an aromatic diamine and a xylylenediamine, the amino groups of said polyamine having been modified at least in part to a secondary amino group of the formula:




wherein R is a hydrogen atom or methyl, and Y is an electron-withdrawing group with the proviso that R cannot represent methyl when the polyamine is an aromatic diamine.

The present invention also provides a method for modifying a polyamine selected from the group consisting of a polyoxyalkylene polyamine, an aromatic diamine and a xylylenediamine, which comprises reacting said polyamine with an ethylenically unsaturated monomer of the formula:




wherein R is a hydrogen atom or methyl and Y is an electron-withdrawing group with the proviso that R cannot represent methyl when the polyamine is an aromatic diamine, to convert the primary amino groups of said polyamine at least partially to a secondary amino group of the formula:



wherein R and y are as defined.

DETAILED DISCUSSION

The production of the polyamine composition of this invention involves the following Michael reaction.



Accordingly, the secondary polyamine formed by this reaction is different in structure from known secondary amines in that the second hydrocarbon substituent of the former contains an electron-withdrawing group.

Starting primary polyamines used in the present invention include polyoxyalkylene polyamines, aromatic diamines and xylylenediamines which are conventionally used in the production of polyurea elastomers and RIM.


Polyoxyalkylene polyamines having a plurality of primary amino groups at the terminals of the molecule may be produced as disclosed, for example, in Belgian Patent No.677124 by the hydrogenolytic ammonolysis of the corresponding polyoxyalkylene polyols. The polyoxyalkylene polyols may be produced, in turn, by addition polymerizing an alkylene oxide such as ethylene oxide, propylene oxide, butylene oxide, tetrahydrofuran or a mixture thereof using an initiator in the presence of a basic catalyst such as alkali metal hydroxides. Usable initiators include water; polyols such as ethylene glycol, di-, tri- or other polyethylene glycols, propylene glycol, di-, tri- or other polypropylene glycols, glycerine, diglycerine, pentaerythritol, sorbitol and sucrose; polyphenols such as bisphenol A, bisphenol S and resorcin; and alkanolamines such as diethanolamine and triethanolamine. Polyoxyalkylene polyols having an average molecular weight from 200 to 10,000, preferable from 400 to 8,000 may be used.

A variety of polyoxyalkylene polyamines are commercially available including polyoxypropylene diamine sold under the name of Jeffamine D-2000 (Texaco Chemical, amine equivalent about 1,000), polyoxypropylene triamines sold under the name of Texrim TR-5050 (Texaco Chemical, amine equivalent about 1930) and Jeffamine T-403 (Texaco Chemical, amine equivalent about 160). These commercial products may advantageously be used in the present invention.

Aromatic diamines usable in the present invention include m- or p-phenylenediamine, 2,4- or 2,6-diaminotoluene, 2,4- or 2,6-diamino-1-methyl-3,5-diethylbenzene, 3-isopropyl-2,6-diaminotoluene, 5-isopropyl-2,4-diaminotoluene, 5-t-butyl-2,4-diaminotoluene, 3-t-butyl-2,6-diaminotoluene, 3,5-diethylthio-2,4-diaminotoluene, 1,3,5-triethyl-2,6-diamino-benzene, 4,4'-diaminodiphenylmethane, 3, 3',5, 5'-tetraethyl-4, 4'-diaminodiphenylmethane, 3, 3', 5, 5'-tetra-propyl-4, 4'-diaminodiphenylmethane, 3, 3'-diethyl-4, 4'-diaminodiphenylether, 3, 4'-diaminodiphenylether, 5, 7-diamino-1, 1-dimethylindan, 4, 6-diamino-1, 1-dimethylindan, 4, 7-diamino-1, 1-dimethylindan, 5, 7-diamino-1, 1, 4, 6-tetra-methylindan, and a mixture of these diamines. A variety of aromatic diamines are commercially available including those sold under the name of Etacure 100 (Asano Chemicals, a mixture of 1-methyl-3, 5-diethyl-2, 4-diaminobenzene and 1-methyl-3, 5-diethyl-2, 6-diaminobenzene), Tolylenediamine (Mitsui Toatsu Chemicals, 2, 4-diaminotoluene) and MDA-220 (Mitsui Toatsu Chemicals, 4, 4'-diaminodiphenylmethane). These commercial products may advantageously be used in the present invention.

The term "xylylenediamine" as used herein includes 1,2-, 1, 3- and 1, 4-isomers and a mixture thereof. Xylylenediamines may be produced by the catalytic hydrogenation of the corresponding dinitriles in the presence of a catalyst such as nickel or cobalt. Commercial products are available including a product sold under the name of Showamine X sold by Showa Denko K.K.

As stated before, the present invention utilizes an ethylenically unsaturated compound or monomer of the formula;



in the Michael reaction with the primary polyamines. Examples of the electron-withdrawing group Y include carboxylate ester residues, ketone residues, cyano, carbamoyl, sulfone residues, sulfonate ester residues and the like. Specific examples of the monomer $\text{CH}=\text{C}(\text{R})-\text{Y}$ includes acrylate esters such as methyl acrylate, ethyl acrylate, propyl acrylate, 2-hydroxyethyl acrylate, 2-hydroxypropyl acrylate, n-butyl acrylate, isobutyl acrylate, t-butyl acrylate, 2-ethylhexyl acrylate, lauryl acrylate and stearyl acrylate; methacrylate esters such as methyl methacrylate, propyl methacrylate, 2-hydroxyethyl methacrylate, 2-hydroxypropyl methacrylate, n-butyl methacrylate, t-butyl methacrylate, 2-ethylhexyl methacrylate, lauryl methacrylate and stearyl methacrylate; other monomers such as acrylonitrile, acrylamide, N,N-dimethylacrylamide, methyl vinyl ketone, ethyl vinyl ketone, methyl vinyl sulfone, ethyl vinyl sulfone, methyl vinylsulfonate and ethyl vinylsulfonate.

We have discovered that the Michael reaction of the primary polyamine and the ethylenic monomer may unexpectedly be promoted by the presence of an acidic or neutral esterification catalyst. Particularly, the presence of such a catalyst is practically imperative when a high conversion rate is desired with a monomer having the formula; $\text{CH}_2=\text{C}(\text{R})-\text{Y}$, wherein R is methyl.

Examples of usable catalysts include inorganic or organic acid such as hydrochloric, sulfuric, nitric, phosphoric, propionic, formic, acetic, dichloroacetic, trichloroacetic, trifluoroacetic, benzoic or p-toluenesulfonic acid; unitary metal oxides such as aluminum oxide, silicon oxide and niobium oxide; complexed metal oxides such as $\text{SiO}_2/\text{Al}_2\text{O}_3$, $\text{TiO}_2/\text{SiO}_2$, $\text{SiO}_2/\text{La}_2\text{O}_3$ and $\text{TiO}_2/\text{Al}_2\text{O}_3$; sulfides such as zinc sulfide; sulfate such as nickel sulfate and copper sulfate; phosphates such as aluminum phosphate and titanium phosphate; chloride such as aluminum chloride and copper chloride; clays such as acid clay, montmorillonite and kaolin; solidified acids such as solidified phosphoric acid, solidified sulfuric acid and solidified boric acid; and acidic ion exchange resins. Also included are organotin compounds such as dibutyltin oxide and dibutyltin dilaurate; organoaluminum compounds such as aluminum isopropylate, mono-sec.-butoxyaluminum diisopropylate, aluminum ethylate, aluminum ethylacetoacetate diisopropylate, aluminum triethylacetoacetate and aluminum bis-ethylacetoacetate monoacetylacetonate; organotitanium compounds such as tetraisopropoxytitanium, tetra-n-butoxytitanium, tetrakis-2-ethylhexoxytitanium, tetrakis-stearyloxytitanium, diisopropoxy-bis(acetylacetonato)titanium, di-n-butoxybis(tri-ethanol-amine)titanium and hydroxybis(lactato)titanium.

We have also discovered that the Michael reaction of the primary polyoxyalkylene polyamine and the ethylenic monomer may be promoted by the presence of a benzenoid compound having at least one electron-donating or electron-withdrawing substituent on the benzenoid ring in place of or in addition to the esterification catalyst. Quinones are also useful for promoting the Michael reaction. Examples of useful benzenoid compounds and quinones include alkyl or aralkyl-substituted benzenoids such as toluene, xylene, ethylbenzene, t-butylbenzene and diphenylmethane; aromatic amines such as aniline, N,N-dimethylaniline, diaminotoluene, xylylene, diaminodiphenylmethane, bis-(N-ethylamino)toluene and aminonaphthalene; hydroxyl compounds such as phenol, cresol and naphthol; halo compounds such as fluorobenzene, chlorobenzene, bromobenzene, iodobenzene, chloronaphthalene and iodonaphthalene; nitro compounds such as nitrobenzene, dinitrotoluene and dinitronaphthalene; cyano compounds such as benzonitrile and naphthonitrile; ketones such as acetophenone and propiophenone; benzenoid compounds having a combination of mentioned substituents; and quinones such as benzoquinone and naphthoquinone.

The ratio of the ethylenic monomer relative to the starting polyamine may vary within a wide range as desired. This ratio in terms of equivalent of ethylenic function relative to the primary amine function may range from 0.01 to 100, preferably from 1 to 10. This means that the presence of an amount of unreacted primary amine functions or ethylenic functions may be tolerated in the reaction mixture.

The amount of the esterification catalysts may vary, when used, but should be no more than the catalytically effective amount.

The amount of aromatic compounds having an electron-donating or withdrawing group should be no more than the tolerable limit in the modified polyoxyalkylene polyamine composition. This amount is generally no more than one equivalent relative to the primary amine function of the starting polyoxyalkylene polyamine.

The Michael reaction may be performed at a temperature from room temperature to about 150°C. After the reaction, the reaction mixture may be used as such as a raw material in the polyurea RIM and the like. If the reaction mixture includes an amount of unreacted ethylenic monomer and/or catalyst, these impurities may be removed by polymerizing, neutralizing or other suitable means.

The following examples are intended to further illustrate the present invention without limiting thereto. All parts and percents therein are by weight unless otherwise indicated.

Example 1

A 500ml flask equipped with a stirrer, reflux condenser, drip funnel, thermometer and nitrogen gas tube was charged with 386g of Texrim TR-5050(trifunctional polyoxyalkylene polyamine, amine equivalent 1930, average MW 5000) and heated to 120 °C. To this was added 73.6g of 2-ethylhexyl acrylate dropwise over 4 hours and allowed to react for additional 24 hours. The conversion rate of the reaction mixture into secondary amine was measured by the salicylaldehyde method according to the modified Wagner method (C.D.Wagner et al., J.Am.Chem.Soc., 69, 2609-2611(1947). The result is shown in Table 1. The conversion rate represent per sent of secondary amine number relative to the total amine number.

Example 2

To the same reactor as used in Example 1 were placed 386g of Texrim TR-5050 and 19.8g of diaminodiphenylmethane. Then 73.6g of 2-ethylhexyl acrylate was added dropwise over 4 hours and allowed to react for additional 36 hours. The conversion rate is shown in Table 1.

Example 3

Example 2 was repeated except that 17.8g of diethyltolylenediamine was replaced for diaminodiphenylmethane. The conversion rate is shown in Table 1.

Example 4

Example 2 was repeated except that 18.6g of aniline was replaced for diaminodiphenylmethane. The conversion rate is shown in Table 1.

Example 5

Example 2 was repeated except that 21.2g of ethylbenzene was replaced for diaminodiphenylmethane. The conversion rate is shown in Table 1.

Example 6

Example 2 was repeated except that 51.2g of n-butyl acrylate was replaced for 2-ethylhexyl acrylate and the reaction was continued for 20 hours. The conversion rate is shown in Table 1.

Example 7

To the same reaction as used in Example 1 were placed 300g of Jeffamine D-2000 (bifunctional polyoxyalkylene polyamine, amine equivalent 1,000, average MW 2000) and 29.7g of diaminodiphenylmethane and heated to 120 °C. To this was added 110.4g of 2-ethylhexyl acrylate dropwise over 4 hours and allowed to react for additional 26 hours. The conversion rate is shown in Table 1.

Example 8

As in Example 7, 300g of Jeffamine D-2000 was reacted with 42g of methyl vinyl ketone in the presence of 26.7g of diethyltolylenediamine at 70 °C for 5 hours. The conversion rate is shown in Table 1.

Example 9

As in Example 7, 300g of Jeffamine D-2000 was reacted with 42.6g of acrylamide in the presence of 29.7g of diaminodiphenylmethane at 80 °C for 28 hours. The conversion rate is shown in Table 1.

Example 10

To the same reactor as used in Example 1 was placed 200g of Jeffamine T-403 (trifunctional polyoxyalkylene polyamine, amine equivalent 160, average MW 400). To this was added 230g of 2-ethylhexyl acrylate dropwise over 2 hours and allowed to react for additional 3 hours. The conversion rate is shown in Table 1.

Example 11

To the same reactor as used in Example 1 were placed 200g of Jeffamine T-403 and 111.3g of diethyltolylenediamine and heated to 70°C. To this was added 66.3g of acrylonitrile dropwise over 4 hours and allowed to react for additional 12 hours. The conversion rate is shown in Table 1.

Example 12

The same reactor as used in Example 1 was charged with 386g of Texrim TR-5050 and 0.6g of acetic acid, and heated to 120°C. To this was added 73.6g 2-ethylhexyl acrylate dropwise over 4 hours and allowed to react for additional 4 hours. The conversion rate is shown in Table 2.

Example 13

Example 12 was repeated except that 1.9g of p-toluenesulfonic acid was replaced for acetic acid. The conversion rate is shown in Table 2.

Example 14

Example 13 was repeated except that 36.8g of 2-ethylhexyl acrylate was added dropwise over 2 hours and allowed to react for additional 6 hours. The conversion rate is shown in Table 2.

Example 15

Example 13 was repeated except that 51.2g of n-butyl acrylate was replaced for 2-ethylhexyl acrylate. The conversion rate is shown in Table 2.

Example 16

Example 13 was repeated except that 56.8g of n-butyl methacrylate was reacted for 32 hours instead of 2-ethylhexyl acrylate. The conversion rate is shown in Table 2.

Example 17

Example 12 was repeated except that 20g of solidified phosphoric acid E48A1 ($P_2O_5/SiO_2/TiO_2$ type sold by JGC Corporation) was replaced for acetic acid. The conversion rate is shown in Table 2.

Example 18

Example 12 was repeated except that 20g of silicaalumina catalyst N631HN (JGC Corporation) was replaced for acetic acid. The conversion rate is shown in Table 2.

Example 19

Example 12 was repeated except that 3.4g of tetrabutoxytitanium was replaced for acetic acid. The conversion rate is shown in Table 2.

Example 20

Example 12 was repeated except that 6.3g of dibutyltin dilaurate was replaced for acetic acid. The conversion rate is shown in Table 2.

Example 21

The same reactor as used in Example 1 was charged with 300g of Jeffamine D-2000 and 2.9g of p-toluenesulfonic acid, and heated to 120°C. To this was added 110.4g of 2-ethylhexyl acrylate dropwise over 4 hours and allowed to react for additional 4 hours. The conversion rate is shown in Table 2.

Example 22

The same reactor used in Example 1 was charged with 200g of Jeffamine T-403 and 11.9g of p-toluenesulfonic acid, and heated to 80 ° C. To this was added 230g of 2-ethylhexyl acrylate dropwise over 2 hours and allowed to react for additional 3 hours. The conversion rate is shown in Table 2.

Example 23

A 500ml flask equipped with a stirrer, reflux condenser, drop funnel, thermometer and nitrogen gas tube was charged with 91.5g of tolylenediamine (bifunctional, amine equivalent 61, MW 122) and 14.3g of p-toluenesulfonic acid, and heated to 120 ° C. To this was added 192g of n-butyl acrylate dropwise over 2 hours and allowed to react for additional 12 hours. The product was tested for the formation and per cent conversion into secondary amine by the FT-IR spectrophotometry, liquid chromatography and ¹³C-NMR. The conversion rate is shown in Table 3.

Example 24

Example 23 was repeated except that 276g of 2-ethylhexyl acrylate was replaced for n-butyl acrylate. The conversion rate is shown in Table 3.

Example 25

As in Example 23, 133.5g of Etacure 100 (diethyltolylenediamine, amine equivalent 89, MW 178 sold by Asano Chemicals Co.,Ltd.) was reacted with 192g of n-butyl acrylate for 24 hours. The conversion rate is shown in Table 3.

Example 26

As in Example 23, 148.5g of MDA-220 (diaminodiphenylmethane, amine equivalent 99, MW 198 sold by Mitsui Toatsu Chemicals, Inc.) was reacted with 192g of n-butyl acrylate for 14 hours. The conversion rate is shown in Table 3.

Example 27

Example 23 was repeated except that 4.5g of acetic acid was replaced for p-toluenesulfonic acid. The conversion rate is shown in Table 3.

Example 28

Example 23 was repeated except that 20g of solidified phosphoric acid E48A1 was replaced for p-toluen -sulfonic acid. The conversion rate is shown in Table 3.

Example 29

A 500 ml flask equipped with a stirrer, reflux condenser, drop funnel, thermometer and nitrogen gas tube was charged with 102g of Showamine X (xylylenediamine, amine equivalent 68, MW 136 sold by Showa Denko K.K.) and heated to 80 ° C. To this was added 276g of 2-ethylhexyl acrylate dropwise over 4 hours and allowed to react for additional 12 hours. The conversion rate into secondary amine was measured by the salicylaldehyde method as in Example 1 and the formation of secondary xylylenediamine was confirmed by the FR-IR spectrophotometry, liquid chromatography and ¹³C-NMR of the reaction mixture after fractional distillation. The conversion rate is shown in Table 4.

Example 30

Example 29 was repeated except that 192g of n-butyl acrylate was replaced for 2-ethylhexyl acrylate. The conversion rate is shown in Table 4.

Example 31

As in Example 29, 204g of Showamine X was reacted with 159g of acrylonitrile at 70° C for 14 hours. The conversion rate is shown in Table 4.

Example 32

Example 29 was repeated except that 210g of methyl vinyl ketone was replaced for 2-ethylhexyl acrylate. The conversion rate is shown in Table 4.

Example 33

The same reactor as used in Example 29 was charged with 51g of Showamine X and 7.1g of p-toluenesulfonic acid, and heated to 80° C. To this was added 213g of n-butyl methacrylate dropwise over 4 hours and allowed to react for additional 20 hours. The conversion rate is shown in Table 4.

Example 34

Example 33 was repeated except that 2.3g of acetic acid was replaced for p-toluenesulfonic acid. The conversion rate is shown in Table 4.

Example 35

Example 33 was repeated except that 10g of silicaalumina catalyst N631HN was replaced for p-toluenesulfonic acid. The conversion rate is shown in Table 4.

Table 1

Example No.	Polyoxyalkylene Polyamine(a)	Monomeric Compound(b)	Aromatic Compd.(c)	Equivalent ratio a:b:c	Reaction temp., °C	Reaction time, hr.	Conversion rate, %
1	TR-5050	2-EHA (1)	—	1:2:0	120	28	38
2	TR-5050	2-EHA	DDM (6)	1:2:1	120	40	86
3	TR-5050	2-EHA	DETA (7)	1:2:1	120	40	87
4	TR-5050	2-EHA	Aniline	1:2:1	120	40	85
5	TR-5050	2-EHA	Ethylbenzene	1:2:1	120	40	85
6	TR-5050	nBA (2)	DDM	1:2:1	120	20	79
7	D-2000	2-EHA	DDM	1:2:1	120	30	84
8	D-2000	MVK (3)	DETA	1:2:1	70	5	78
9	D-2000	AAM (4)	DDM	1:2:1	80	28	35
10	T-403	2-EHA	—	1:1:0	80	5	80
11	T-403	AN (5)	DETA	1:2:1	70	16	79

Footnote of Table 1

- (1) 2-Ethylhexyl acrylate (5) Acrylonitrile
 (2) n-Butyl acrylate (6) Diaminodiphenylmethane
 (3) Methyl vinyl ketone (7) Diethyltolylenediamine
 (4) Acrylamide

Table 2

Example No.	Polyoxyalkylene Polyamine(a)	Monomeric Compound(b)	Aromatic Compd. (c)	Equivalent ratio a:b:c	Reaction temp., °C	Reaction time, hr.	Conversion rate, %
12	TR-5050	2-EHA	ACOH	1:2:0.05	120	8	96
13	TR-5050	2-EHA	PTS (1)	1:2:0.05	120	8	97
14	TR-5050	2-EHA	PTS	1:1:0.05	120	8	80
15	TR-5050	nBA	PTS	1:2:0.05	120	8	95
16	TR-5050	nBMA (4)	PTS	1:2:0.05	120	32	52
17	TR-5050	2-EHA	E48A1	1:2:x (3)	120	8	90
18	TR-5050	2-EHA	N631HN	1:2:x	120	16	57
19	TR-5050	2-EHA	Ti (OBu) ₄	1:2:0.05	120	16	60
20	TR-5050	2-EHA	DBTDL (2)	1:2:0.05	120	12	97
21	D-2000	2-EHA	PTS	1:2:0.05	120	8	97
22	T-403	2-EHA	PTS	1:2:0.05	80	3	98

Footnote of Table 2

- (1) p-Toluenesulfonic acid
 (2) Dibutyltin dilaurate
 (3) Not applicable
 (4) n-Butyl methacrylate

Table 3

Example No.	Polyamine(a)	Monomeric Compound(b)	Aromatic Compd.(c)	Equivalent ratio a:b:c	Reaction temp., °C	Reaction time, hr.	Conversion rate, %
23	TDA (1)	nBA	PTS	1:1:0.05	120	14	98
24	TDA	2-EHA	PTS	1:1:0.05	120	14	95
25	E-100	nBA	PTS	1:1:0.05	120	24	70
26	MDA-200	nBA	PTS	1:1:0.05	120	14	84
27	TDA	nBA	AcOH	1:1:0.05	120	14	96
28	TDA	nBA	E48A1	1:1:x (2)	120	14	90

Footnote of Table 3

(1) Tolylenediamine

(2) Not applicable

Table 4

Example No.	Polyamine(a)	Monomeric Compound(b)	Aromatic Compd.(c)	Equivalent ratio a:b:c	Reaction temp., °C	Reaction time, hr.	Conversion rate, %
29	Showamine X	2-EHA	—	1:1:0	80	14	87
30	Showamine X	nBA	—	1:1:0	80	14	92
31	Showamine X	AN	—	1:1:0	70	14	94
32	Showamine X	MVK	—	1:1:0	70	14	90
33	Showamine X	nBMA	PTS	1:2:0.05	80	24	91
34	Showamine X	nBMA	AcOH	1:2:0.05	80	24	91
35	Showamine X	nBMA	N631HN	1:2:x (1)	80	24	72

Footnote of Table 4

(1) Not applicable

Example 36

- 55 To the same flask as used in Example 1 were placed 386g of Texrim TR-5050 and heated to 120°C. To this was added 52g of 2-hydroxypropyl acrylate dropwise over 4 hours. A coversin rate of 98% was reached at the end of addition.

Claims

1. A polyamine composition for use in the manufacture of plastics comprising a member selected from the group consisting of a polyoxyalkylene polyamine, an aromatic diamine and a xylylenediamine, the amino groups of said polyamine having been modified at least in part to a secondary amino group of the formula:

$$\text{-NH-CH}_2\text{-CH(R)-Y}$$
 wherein R is a hydrogen atom or methyl, and Y is an electron-withdrawing group with the proviso that R cannot represent methyl when the polyamine is an aromatic diamine.
2. The polyamine composition according to Claim 1, wherein at least 30% of said amino groups are said secondary amino group.
3. The polyamine composition according to Claim 2, said electron-withdrawing group is a carboxylate or sulfonate residue, a ketone residue, cyano, carbamoyl, or a sulfone residue.
4. The polyamine composition according to Claim 3, wherein said polyoxyalkylene polyamine is a polyoxypropylene di- or triamine having an average molecular weight from about 200 to about 10,000.
5. The polyamine composition according to Claim 3, wherein said aromatic diamine is tolylenediamine, diethyltolylenediamine or diaminodiphenylmethane.
6. The polyamine composition according to Claim 3, wherein said xylylenediamine is 1,2-, 1,3- or 1,4-isomer, or a mixture thereof.
7. A method for modifying a polyamine selected from the group consisting of a polyoxyalkylene polyamine, an aromatic diamine and a xylylenediamine, which comprises reacting said polyamine with an ethylenically unsaturated monomer of the formula:

$$\text{CH}_2 = \text{C(R)-Y}$$
 wherein R is a hydrogen atom or methyl, and Y is an electron-withdrawing group with the proviso that R cannot represent methyl when the polyamine is an aromatic diamine, to convert the primary amino groups of said polyamine at least partially to a secondary amino group of the formula:

$$\text{-NH-CH}_2\text{-CH(R)-Y}$$
 wherein R and Y are as defined.
8. The method according to Claim 7, wherein at least 30% of said primary amino groups are converted to said secondary amino group.
9. The method according to Claim 7, wherein said ethylenically unsaturated monomer is an acrylate ester, a methacrylate ester, acrylonitrile, acrylamide, N, N-dimethylacrylamide, methyl vinyl ketone, ethyl vinyl ketone, methyl vinyl sulfone, ethyl vinyl sulfone, methyl vinylsulfonate or ethyl vinylsulfonate.
10. The method according to Claim 7, wherein said polyoxyalkylene polyamine is a polyoxypropylene di- or triamine having an average molecular weight from about 200 to about 10,000.
11. The method according to Claim 7, wherein said aromatic diamine is tolylenediamine, diethyltolylenediamine or diaminodiphenylmethane.
12. The method according to Claim 7, wherein said xylylenediamine is the 1,2-, 1,3- or 1,4-isomer, or a mixture thereof.
13. The method according to Claim 7, wherein said reaction is carried out in the presence of an acidic or

neutral esterification catalyst.

14. The method according to Claim 13, wherein said esterification catalyst is an organic or inorganic acid; a unitary or complexed metal oxide acting as a solid acid; a sulfide, sulfate, phosphate or chloride of a metal; a clay; a solidified acid; an acidic ion exchange resin; or an organic tin-, aluminum- or titanium compound.
15. The method according to Claim 10, wherein said reaction is carried out in the presence of a benzenoid compound having an electron-donating or electron-withdrawing substituent on the benzenoid ring, or a quinone.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 499 206 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **92102265.3**(51) Int. Cl.⁵: **C08G 65/32, C07C 229/18**(22) Date of filing: **11.02.92**

(30) Priority: **12.02.91 JP 41324/91**
30.04.91 JP 128417/91
30.04.91 JP 128418/91

(43) Date of publication of application:
19.08.92 Bulletin 92/34

(84) Designated Contracting States:
DE FR GB

(88) Date of deferred publication of the search report:
03.03.93 Bulletin 93/09


(71) Applicant: **NIPPON PAINT CO., LTD.**
1-2, Oyodokita 2-chome Kita-ku
Osaka-shi(JP)

(72) Inventor: **Ohshima, Toshiyuki**
4-25-20 Ayukawa
Ibaraki-shi, Osaka-fu(JP)
Inventor: **Ishibashi, Hideo**
24-10 Nakakandacho
Neyagawa-shi, Osaka-fu(JP)
Inventor: **Tamura, Rie**
2-1-1-611 Shoji
Toyonaka-shi, Osaka-fu(JP)
Inventor: **Yamamoto, Satoshi**
2-10-10 Nagaohigashimachi
Hirakata-shi, Osaka-fu(JP)
Inventor: **Izumo, Takaharu**
789 Yamazaki, Shlmamoto-cho
Mishima-gun, Osaka-fu(JP)

(74) Representative: **Kinzebach, Werner, Dr. et al**
Patentanwälte Reitstötter, Kinzebach und
Partner Sternwartstrasse 4 Postfach 86 06 49
W-8000 München 86 (DE)

(54) **Polyamine compositions containing secondary amine functions.**

(57) Polyoxyalkylene polyamine or aromatic diamines or xylylenediamines are modified by subjecting to the Michael reaction with an ethylenically unsaturated monomer having an electron-withdrawing group to convert the primary amino groups at least in part to a secondary amino group of the formula:



wherein R is a hydrogen atom or methyl, and Y is an electron-withdrawing group. The modified amines find use in the manufacture of plastics such as polyurea elastomers or polyurea RIM.

EP 0 499 206 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 10 2265

DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	EP-A-0 046 088 (MITSUI-TEXACO CHEMICALS COMPANY) * page 1, line 32 - page 2, line 27; page 3, line 13 - line 36; examples; claims 1-3, 5, 6 *	1-4,7-10	C08G65/32 C07C229/18
X	EP-A-0 103 211 (AMERICAN HOECHST CORPORATION) * page 7, line 31 - page 8, line 3; claims 1,9; examples 2,20 *	1,7,13,14	
A,D	DATABASE WPIL Week 9046, Derwent Publications Ltd., London, GB; AN 90-346091 & JP-A-02 251 515 (DAINIPPON INK. CHEM.) * abstract *	1,7	
A	DATABASE WPIL Week 8402, Derwent Publications Ltd., London, GB; AN 84-008043 & JP-A-58 201 868 (DAINIPPON INK. CHEM.) * abstract *	1,7	TECHNICAL FIELDS SEARCHED (Int. Cl.5)
P,X	US-A-5 075 503 (J.-J. LIN G. P. SPERANZA) * column 3, line 33 - column 4, line 21; example 1a *	1-3,7-9	C07C C08G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 11 DECEMBER 1992	Examiner SEUFERT G.H.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons * : member of the same patent family, corresponding document	

EPO FORM 150 (04/81) (P0401)